

AMENDMENTS TO THE SPECIFICATION:

Please amend the indicated paragraphs of the specification in accordance with the amendments indicated below.

Page 5, first full paragraph, amend as indicated below:

Table 1

		Comparative Example			Inventive Example			Comparative Example			Inventive Example		
		1	2	3	1	2	3	4	5	6	4	5	6
Compounding ratio (mass%)	graphite (0.5 mm \geq)	25	35	35	25	35	35	10	—	—	10	—	—
	dolomite clinker (1 mm \geq)	20	15	15	20	15	15	—	—	—	—	—	—
	dolomite clinker (0.2 mm \geq)	35	30	30	35	30	30	35	40	40	35	40	40
	dolomite clinker (0.074 mm \geq)	20	20	—	20	20	—	35	35	—	35	35	—
	magnesia clinker (0.074 mm \geq)	—	—	20	—	—	20	—	—	35	—	—	35
	calcia clinker (1 mm \geq)	—	—	—	—	—	—	20	25	25	20	25	25
Application of CO ₂ treatment to clinker *1		NON NO	NON NO	NON NO	YES	YES	YES	NON NO	NON NO	NON NO	YES	YES	YES
Presence of cracks after burning process		YES	YES	YES	NON NO	NON NO	NON NO	YES	YES	YES	NON NO	NON NO	NON NO